


TWINLIGHT BLUES

Twinlight Blues is a rich fabric design that has a striking zigzag texture. Its stripe pattern combined with dynamic and fashionable color combinations give a dramatic and stylish edge to your interior.

TRANSLUCENT




ALSO AVAILABLE AS ROLLER FABRIC



GENERAL INFORMATION

Number of Colors	9	
Material Composition	100% Polyester	
Solid	7,5 cm	2.95 in
Sheer	5 cm	1.97 in
Width	280 cm	110.00 in
Thickness (+/- 5%)	0,46 mm	0.0181 in
Weight (+/- 5%)	150 gr/m ²	4.42 oz/yd ²
Roll Length	50 m	54.68 yd



SPECIAL VALUES

Color Fastness to Light	5 - 6 (DIN ISO 105-B02)	Tensile Strength in Weft	1444 N (ISO 13934-2)
Finish	Heat Setting	Tearing Strength in Warp	4,8 N (ISO 13937-1)
PVC Free	Yes	Tearing Strength in Weft	6,7 N (ISO 13937-1)
Lead Free	Yes	Manufacturing Procedure	Cold Cut / Crush cut
Halogen Free	Yes	Care Instructions	Damp Cloth
Formaldehyde Free	Yes		
Phthalates Free	Yes		

SUITABLE FOR



Twinlight

CARE & HANDLING

Remove dust with vacuum cleaner or compressed air. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge, soft brush or cloth. Leave the blind down until completely dry.

Version 20250718



The technical data above are average values with a +/- 5% tolerance. The values quotes above represent results of standards and internal tests performed and are provided for information only to enable to make the best use of our products. Our products are subjects to technical evolutions, we remain entitled to modify the characteristics of our products at any time. Actual product color may vary slightly from colors shown on this technical data sheet.

THERMAL AND VISUAL PROPERTIES | DIN EN 410, EN ISO 52022-1, DIN EN 14501

Item Number	Color	Rs	Ts	As	Rv	Tv	Av	Tuv
ECB 280.004	Ice White	75,86%	21,06%	3,08%	75,90%	19,56%	4,54%	17,20%
ECB 280.004	Ice White transp.	10,27%	88,16%	1,57%	10,40%	87,66%	1,94%	82,10%
ECB 280.005	Cloud	64,35%	14,95%	20,70%	54,30%	8,49%	37,21%	2,40%
ECB 280.009	Gunmetal	44,95%	10,33%	44,72%	14,40%	0,14%	85,46%	0,20%

Rs = Solar Reflection **Tv** = Light Transmittance **Ts** = Solar Transmittance
Rv = Light Reflection **Av** = Light Absorption **As** = Solar Absorption
TUV = Ultraviolet Transmittance

Item Number	Color	Glass type C			Glass type E			Glass type F			Glass type G		
		U _g =1,2 W/(m²K) g=0,59			U _g =0,8 W/(m²K) g=0,55			U _g = 1.1 W/(m²K) g=0,64			U _g = 1.0 W/(m²K) g=0,33		
		Gtot	Gtot Class	Fc	Gtot	Gtot Class	Fc	Gtot	Gtot Class	Fc	Gtot	Gtot Class	Fc
ECB 280.004	Ice White	0,3252	2	0,5512	0,3201	2	0,5820	0,3286	2	0,5134	0,2471	2	0,7487
ECB 280.004	Ice White transp.	0,5539	0	0,9388	0,5187	0	0,9431	0,5976	0	0,9337	0,3186	2	0,9656
ECB 280.005	Cloud	0,3613	1	0,6124	0,3524	1	0,6407	0,3717	1	0,5808	0,2577	2	0,7810
ECB 280.009	Gunmetal	0,4234	1	0,7176	0,4076	1	0,7412	0,4458	1	0,6965	0,2763	2	0,8372

Gtot Value = The total transmission value of solar energy through a combination of window and sun protection
FC-Value = Reduction factor (from 0-1) of the fabric concerning solar energy
Glass type C = Double glazing, with low emissivity and argon cavity
Glass type E = Triple glazing with low emissivity and argon cavity
Glass type F = Double glazing with low-emissivity coating on position 3, with 90% argon-filled spacer
Glass type G = Solar control glazing with 90% argon-filled spacer

COLORS




ECB 280.004
Ice White



ECB 280.005
Cloud



ECB 280.009
Gunmetal



ECB 280.001
Ivory




ECB 280.002
Cream



ECB 280.003
Chocolate



ECB 280.006
Neutral Gray



ECB 280.007
Castor Gray



ECB 280.008
Rock Ridge

Scan the QR-code for more information



Twinlight Blues

Version 20250718